


Stretch at	90°	45°	0°	HTP [®] plus
10 lbs	1,5	3,7	2,6	
10 lbs flutter	1,5	3,7	2,8	
40 lbs	5,8	16,4	11,5	
200 lbs				
1% elongation (lbs)	83,4			



Stretch at	90°	45°	0°	MTO
10 lbs	1,5	9,4	4,4	
10 lbs flutter	1,5	10,2	4,6	
40 lbs	6,7	44,5	18,6	
200 lbs				
1% elongation (lbs)	79,9			

Style	Finish	Actual weight		Construction	Typical specs. Fill - Bias at 10 lbs	Bias range
		G/m ²	Sm-oz			
230 SF 5.4 oz	HTP [®] plus	240	5,6	125 x 380 High Aspect	1,5 - 3,7	under 20,0 at 40 lbs
	HMTO	236	5,5		1,5 - 7,0	5,0 - 8,0
	MTO	236	5,5		1,5 - 9,4	8,0 - 13,0