


Stretch at	90°	45°	0°	HTP [®] plus
10 lbs	1,1	3,7	2,1	
10 lbs flutter	1,1	3,8	2,2	
40 lbs	5,6	15,6	10,9	
200 lbs				
1% elongation (lbs)	96,3			



Stretch at	90°	45°	0°	MTO
10 lbs	1,4	9,5	3,6	
10 lbs flutter	1,5	10,4	4,0	
40 lbs	5,7	43,6	13,9	
200 lbs				
1% elongation (lbs)	89,5			

Style	Finish	Actual weight		Construction	Typical specs. Fill - Bias at 10 lbs	Bias range
		G/m ²	Sm-oz			
260 SF 6.1 oz	HTP [®] plus	261	6,1	125 x 500 High Aspect	1,4 - 3,7	under 20,0 at 40 lbs
	HMTO	258	6,0		1,4 - 6,7	5,0 - 8,0
	MTO	258	6,0		1,4 - 9,5	8,0 - 13,0