


Stretch at	90°	45°	0°	HTP [®] plus
10 lbs	1,1	3,0	1,8	
10 lbs flutter	1,3	3,3	1,8	
40 lbs	5,3	14,1	7,8	
200 lbs				
1% elongation (lbs)	99,3			



Stretch at	90°	45°	0°	MTO
10 lbs	1,9	8,9	3,9	
10 lbs flutter	2,0	10,3	4,7	
40 lbs	7,2	39,0	15,5	
200 lbs				
1% elongation (lbs)	81,5			

Style	Finish	Actual weight		Construction	Typical specs.		Bias range
		G/m ²	Sm-oz		Fill	Bias at 10 lbs	
300 SF 7.0 oz	HTP [®] plus	310	7,2	200 x 500 High Aspect	1,3	3,5	under 15,0 at 40 lbs 5,0 - 8,0 8,0 - 13,0
	HMTO	307	7,1		1,5	6,4	
	MTO	305	7,1		1,9	8,9	