


Stretch at	90°	45°	0°
10 lbs	0,7	5,8	3,4
10 lbs flutter	0,7	7,5	4,0
40 lbs	3,5	28,0	14,6
200 lbs	29,9		
1% elongation (lbs)	135,3		

HTP® Plus



Stretch at	90°	45°	0°
10 lbs	0,9	9,7	4,0
10 lbs flutter	0,9	10,4	4,1
40 lbs	3,6	48,4	15,2
200 lbs	34,9		
1% elongation (lbs)	129,8		

MTO

Style	Finish	Actual weight		Construction	Typical specs. Fill - Bias at 10 lbs	Bias range
		G/m ²	Sm-oz			
390 SF 9.2 oz	HTP® plus	385	9,0	250 x 1000 High Aspect	0,6 - 5,5	under 15,0 at 40 lbs
	HMTO	377	8,8		0,7 - 5,8	5,0 - 8,0
	MTO	375	8,7		0,9 - 9,7	8,0 - 13,0